


Lumirror® 45.16

Application

- Advertising
- Graphic arts (banners, displays...)
- Labels



CLEAR ASYMMETRICAL PET
FILM WITH TWO SIDES TREATED

Benefits

- Clear film
- Good adhesion with various types of coatings (inks, adhesives...) on acrylic side
- Antistatic properties with anti-dust effect
- High dimensional stability
- Excellent machinability

Toray Films Europe SAS,
Place d'Arménie,
01700 Saint-Maurice-de-Beynost, FRANCE

To access Toray Films Europe's **certifications list**, please visit
www.torayfilms.eu/en/certifications

Typical Values *(These values do not constitute binding specifications)*

Properties	Test Method	Unit	96 µm	175 µm		
YIELD						
Unit Weight		g/m ²	134.4	245.0		
Area Yield		m ² /kg	7.4	4.1		
MECHANICAL						
Tensile Strength MD	ASTM D882	daN/mm ²	21	19		
Elongation at Break MD					%	140
THERMAL						
Shrinkage 150°C 30mn MD	Internal Method	%	1.5	1.5		
Shrinkage 150°C 30mn TD					0.6	0.6
OPTICAL						
Gardner Haze	ASTM D1003	%	2	2		
SURFACE						
Roughness Ra	Internal Method	nm	9	9		
Roughness Rz					274	226
Half time decay					s	2.1


Regulation

Lumirror® 45.16 does **not** comply with European legal requirements of food contact applications due to its specific treatment. For Toray's certification concerning specific applications with each product, please refer to the 'Declaration of Compliance'.

Presentation of the rolls

Roll packaging: The rolls are suspended on standard paper core with internal diameter of 152.8mm. For all presentation, minimum roll width = 340mm and maximum roll width = 3400mm.

Returnable packaging: Wooden flanges, plastic flanges and pallets are returnable. The treated side is identified on the roll label.



Please contact us for...

- Any other presentation (width, length, core)
- Process for returnable packaging
- Any other information about typical values, measuring conditions, tolerances, deliveries...

Lumirror® is a registered trademark of Toray Films Europe SAS - TFE March 2023

DISCLAIMER: This leaflet is provided for informational purpose only and is not binding, nor can it constitute specifications to the buyer. The information contained in this document is based on numerous tests and trials we have carried out in our laboratories. Deviations from the results thus obtained can therefore be experienced depending on the actual conditions of use. This document does not provide any guarantee with regard to compliance of our product with the typical values indicated, nor does it provide any guarantee as the suitability of our products for any particular use.