


Lumirror® 60.13

Application

- Mat surface transfer
- Carrier film



MATT PET FILM

Benefits

- Controlled permanent mat levels
- High dimensional stability
- Good flatness
- Excellent machinability and performance due to calibrated roughness

Toray Films Europe SAS,
Place d'Arménie,
01700 Saint-Maurice-de-Beynost, FRANCE

To access Toray Films Europe's **certifications list**, please visit
www.torayfilms.eu/en/certifications

Typical Values *(These values do not constitute binding specifications)*

Properties	Test Method	Unit	50 µm	75 µm
YIELD				
Unit Weight		g/m ²	70	105
Area Yield		m ² /kg	14.3	9.5
MECHANICAL				
Tensile Strength MD	ASTM D 882	daN/mm ²	19	16
Elongation at Break MD		%	120	90
THERMAL				
Shrinkage 150°C 30mn MD	Internal Method	%	1.3	1.3
Shrinkage 150°C 30mn TD			0.5	0.5
OPTICAL				
Total Light Transmission	ASTM D1003	%	70	60
Gardner Haze			97	100
Gloss at 60°	ASTM D523		30	33
SURFACE				
Roughness Ra	Internal Method	nm	220	220
Roughness Rz			1 900	2 100

Regulation

Lumirror® 60.13 does not comply with European applicable requirements for food contact applications. For Toray's certification concerning specific applications with each product, please refer to the 'Declaration of Compliance'.

Presentation of the rolls

Roll packaging: The rolls are suspended on standard paper core with internal diameter of 152.8mm. For all presentation, minimum roll width = 340mm and maximum roll width = 2100mm.

Returnable packaging: Wooden flanges, plastic flanges and pallets are returnable.

Please contact us for...

- Any other presentation (width, length, core)
- Process for returnable packaging
- Any other information about typical values, measuring conditions, tolerances, deliveries...

Lumirror® is a registered trademark of Toray Films Europe SAS - TFE March 2023

DISCLAIMER: This leaflet is provided for informational purpose only and is not binding, nor can it constitute specifications to the buyer. The information contained in this document is based on numerous tests and trials we have carried out in our laboratories. Deviations from the results thus obtained can therefore be experienced depending on the actual conditions of use. This document does not provide any guarantee with regard to compliance of our product with the typical values indicated, nor does it provide any guarantee as the suitability of our products for any particular use.